



515

DESCRIPTION:

Rust Converter and Steel Preparer. Reacts with rust and corrosion converting rust to iron phosphate. Treatment with 515 leaves a stable corrosion resistant surface ready for painting.

CHARACTERISTICS:

Corrosion Effectively Retarded

Mainlube 515 reacts on existing rust and corrosion chemically converting the rust to protective iron phosphate ready to accept the primer. This effectively retards existing and future corrosion.

Primer Adherence Improved.

515's Chemically manufactured film of corrosion inhibitor leaves a slight tackiness, improving the adhesion of a primer. This prevents undercutting of the paint film by subsequent rust.

Extends Paint Life

When exposed metal is treated with Mainlube 515 before priming paint life is lengthened 3 times or more. Corrosion of exposed surfaces due to paint damage is prevented when steel is pretreated with Mainlube 515.

Converts Oxides

Mainlube 515 converts the Oxides of Iron (Rust) to an Iron Phosphate that is an excellent rust inhibitor. The Phosphate base also yields a greatly improved bond between the steel surface and the priming paint.

How To Apply

The surface should be free of oil, grease or paint. Loose rust should be removed by wire brushing or scraping. Application can be made by brush, spray, roller or dip.

Apply Mainlube 515 to all exposed areas with emphasis on pitted areas. On conversion the surfaces should turn white, grey or black, *it should not have a rusty appearance.*

Application

Light Rust	One Part Of Mainlube 515 To Two Parts Water
Medium Rust	One Part Of Mainlube 515 To One Parts Water
Extreme Rust	Apply Undiluted, Reapply To Difficult Areas After 45 Mins.

No neutralisation or flushing is required after application with Mainlube 515 as the Rust inhibiting layer left prevents further rusting.

Mainlube 515 is nonflammable, non fuming and can be applied to operating equipment. For best long term results Mainlube 515 should be top coated.

CAUTION CONTAINS ACIDS

Keep out of reach of children. Avoid contact with skin.

If contact with skin occurs, flush with water for 15 minutes.

If contact with eyes occurs, flush with water for 15 minutes and seek medical advice.

MAINLUBE SUPERIOR MAINTENANCE LUBRICANTS PTY LIMITED
ACN 001-748-876 SYDNEY AUSTRALIA

DISTRIBUTED BY:



SB515--1 ACAC